



© 2024 M-A Ruel

[maruel.ca](http://maruel.ca)

	PETG Basic*	PETG PETG-HF	PETG Translucent	PETG PETG-CF	ABS ABS	ABS ABS-GF	ASA ASA	ASA Aero	ASA ASA-CF
Price AUD	N/A	31 \$/kg	31 \$/kg	49 \$/kg	31 \$/kg	46 \$/kg	46 \$/kg	77 \$/kg	57 \$/kg
4x refill AUD		23 \$/kg	23 \$/kg		23 \$/kg				
Density	1.25g/cm³	1.28g/cm³	1.25g/cm³	1.25g/cm³	1.05g/cm³	1.08g/cm³	1.05g/cm³	0.99g/cm³	1.02g/cm³
Heat resistance	69 °C	69 °C	74 °C	74 °C	87 °C	99 °C	100 °C	85 °C	110 °C
Saturated water	0.32%	0.40%	0.30%	0.30%	0.65%	0.53%	0.45%	0.80%	0.33%
Young's Modul XY	1.5 GPa	1.8 GPa	1.4 GPa	2.5 GPa	2.2 GPa	3.2 GPa	2.5 GPa	2.0 GPa	4.2 GPa
Young's Modul Z	1.1 GPa	1.5 GPa	1.2 GPa	1.3 GPa	2.0 GPa	2.3 GPa	2.1 GPa	1.2 GPa	2.3 GPa
Tensile Stren XY	32 MPa	34 MPa	33 MPa	35 MPa	33 MPa	36 MPa	37 MPa	32 MPa	34 MPa
Tensile Stren Z	28 MPa	23 MPa	29 MPa	29 MPa	28 MPa	29 MPa	31 MPa	21 MPa	30 MPa
Bending Modul XY	1.7 GPa	2.1 GPa	1.6 GPa	2.9 GPa	1.9 GPa	2.9 GPa	1.9 GPa	1.5 GPa	3.7 GPa
Bending Modul Z	1.3 GPa	1.8 GPa	1.5 GPa	1.6 GPa	1.6 GPa	2.0 GPa	1.7 GPa	1.2 GPa	1.4 GPa
Bending Stren XY	65 MPa	64 MPa	68 MPa	70 MPa	62 MPa	68 MPa	65 MPa	58 MPa	72 MPa
Bending Stren Z	48 MPa	48 MPa	55 MPa	48 MPa	39 MPa	46 MPa	40 MPa	24 MPa	33 MPa
Impact Strength XY	53 kJ/m²	32 kJ/m²	37 kJ/m²	41 kJ/m²	39 kJ/m²	15 kJ/m²	41 kJ/m²	32 kJ/m²	14 kJ/m²
Impact Strength Z	14 kJ/m²	11 kJ/m²	7 kJ/m²	11 kJ/m²	7 kJ/m²	5 kJ/m²	5 kJ/m²	3 kJ/m²	9 kJ/m²
UV resistance	★★★★	★★★★	★★★★	★★★★	★	★	★★★★★	★★★★★	★★★★★
Drying required		🔥	🔥	🔥 (opt)		🔥		🔥	🔥
Drying oven	65°C, 8h	65°C, 8h	65°C, 8h	65°C, 8h	80°C, 8h	80°C, 8h	80°C, 8h	80°C, 8h	80°C, 8h
Drying heatbed	80°C, 12h	80°C, 12h	80°C, 12h	80°C, 12h	95°C, 12h	95°C, 12h	95°C, 12h	95°C, 12h	95°C, 12h
AMS compatible	✓	✓	✓	✓ (🚫 lite)	✓ (🚫 lite)	✓ (🚫 lite)	✓ (🚫 lite)	✓ (🚫 lite)	✓ (🚫 lite)
Liquid Glue	✓	✓	✓	✓	✓	✓	✓	✓	✓
Abrasive				⚙️					
Warps					↓	(less)	↓	↓	(less)
Layer adhesion	14 kJ/m²	11 kJ/m²		11 kJ/m²	7 kJ/m²↓	5 kJ/m²↓	5 kJ/m²↓		9 kJ/m²↓
Nozzle / hardened	>=0.4mm	All	All	>=0.4 ⚙️	All	>=0.4mm ⚙️	=0.4 ⚙️	=0.4mm	>=0.4 ⚙️
Build plate	🔥🔥	❄️🔥🔥	❄️🔥🔥	🔥🔥	🔥🔥	🔥🔥	🔥🔥	🔥🔥	🔥🔥
Print speed	200mm/s	300mm/s	220mm/s	200mm/s	300mm/s	180mm/s	250mm/s	150mm/s	250mm/s
Max Volum flow	13mm³/s	21mm³/s	6mm³/s	12mm³/s	16mm³/s	12mm³/s	18mm³/s	12mm³/s	18mm³/s
Tips	<a href="#">Tips</a>					use 0.6mm	Outdoor	Slow&Hot!	use 0.6mm
Annealing	65°C 8h	75°C 8h	65°C 8h	65°C 8h	80°C 12h	80°C 12h	80°C 12h	80°C 12h	80°C 12h

© 2024 M-A Ruel

[maruel.ca](http://maruel.ca)

	TPU	TPU	TPU	PC	PC	PA	PA	PA	PPA	PET
	<a href="#">TPU 95A*</a>	<a href="#">TPU 95A HF</a>	<a href="#">68D for AMS</a>	<a href="#">PC</a>	<a href="#">PC-FR</a>	<a href="#">PA6-CF</a>	<a href="#">PA6-GF</a>	<a href="#">PAHT-CF</a>	<a href="#">PPA-CF</a>	<a href="#">PET-CF</a>
<b>Price AUD</b>	N/A	64 \$/kg	60 \$/kg	62 \$/kg	84 \$/kg	123 \$/kg 💰	92 \$/kg	145 \$/kg 💰	307 \$/kg 💰	130 \$/kg 💰
<b>4x refill AUD</b>										
<b>Density</b>	1.20g/cm <sup>3</sup>	1.22g/cm <sup>3</sup>	1.26g/cm <sup>3</sup>	1.20g/cm <sup>3</sup>	1.18g/cm <sup>3</sup>	1.09g/cm <sup>3</sup>	1.14g/cm <sup>3</sup>	1.06g/cm <sup>3</sup>	1.25g/cm <sup>3</sup>	1.29g/cm <sup>3</sup>
<b>Heat resistance</b>	185 °C	183 °C	183 °C	112 °C	108 °C	186 °C	182 °C	194 °C	227 °C	205 °C
<b>Saturated water</b>	1.16%	1.08%	1.20%	0.25%	0.12%	2.35%	2.56%	0.88%	1.30%	0.37%
<b><a href="#">Young's Modul XY</a></b>	🧐	🧐	1.2 GPa	2.1 GPa	1.7 GPa	4.4 GPa	2.9 GPa	3.9 GPa	<b>11.8 GPa</b>	4.7 GPa
<b>Young's Modul Z</b>			.6 GPa	1.5 GPa	1.5 GPa	2.2 GPa	2.0 GPa	2.2 GPa	<b>4.3 GPa</b>	2.2 GPa
<b>Tensile Stren XY</b>	30 MPa	27 MPa	22 MPa	55 MPa	60 MPa	102 MPa	75 MPa	92 MPa	<b>168 MPa</b>	74 MPa
<b>Tensile Stren Z</b>	23 MPa	22 MPa	11 MPa	34 MPa	21 MPa	48 MPa	27 MPa	47 MPa	57 MPa	35 MPa
<b>Bending Modul XY</b>	🧐	🧐	🧐	2.3 GPa	1.9 GPa	5.5 GPa	3.7 GPa	3.9 GPa	9.9 GPa	5.3 GPa
<b>Bending Modul Z</b>				1.6 GPa	1.7 GPa	2.2 GPa	2.3 GPa	2.2 GPa	3.2 GPa	2.2 GPa
<b>Bending Stren XY</b>				108 MPa	90 MPa	151 MPa	120 MPa	<b>4.2 GPa</b>	208 MPa	131 MPa
<b>Bending Stren Z</b>				55 MPa	47 MPa	80 MPa	51 MPa	<b>1.8 GPa</b>	63 MPa	49 MPa
<b>Impact Strength XY</b>	125 kj/m <sup>2</sup>	123 kj/m <sup>2</sup>	124 kj/m <sup>2</sup>	35 kj/m <sup>2</sup>	55 kj/m <sup>2</sup>	40 kj/m <sup>2</sup>	27 kj/m <sup>2</sup>	58 kj/m <sup>2</sup>	42 kj/m <sup>2</sup>	36 kj/m <sup>2</sup>
<b>Impact Strength Z</b>	89 kj/m <sup>2</sup>	86 kj/m <sup>2</sup>	10 kj/m <sup>2</sup>	9 kj/m <sup>2</sup>	8 kj/m <sup>2</sup>	16 kj/m <sup>2</sup>	4 kj/m <sup>2</sup>	13 kj/m <sup>2</sup>	4 kj/m <sup>2</sup>	5 kj/m <sup>2</sup>
<b>UV resistance</b>	☆☆☆	☆☆☆	☆☆☆	☆	☆		☆	☆	☆	☆☆☆☆
<b>Drying required</b>	🔥	🔥	🔥	🔥	🔥	🔥	🔥	🔥	🔥	🔥
<b>Drying oven</b>	70°C, 8h	70°C, 8h	70°C, 8h	80°C, 8h	80°C, 8h	80°C, 12h	80°C, 12h	80°C, 12h	120°C, 12h	80°C, 12h
<b>Drying heatbed</b>	85°C, 12h	85°C, 12h	85°C, 12h	95°C, 12h	95°C, 12h	95°C, 12h	95°C, 12h	95°C, 12h		95°C, 12h
<b>AMS compatible</b>	🚫	🚫	✓	✓ (🚫 lite)	✓ (🚫 lite)	🚫	✓ (🚫 lite)	✓ (🚫 lite)	🚫	🚫
<b>Liquid Glue</b>	✓	✓	✓	🚫	🚫	🚫	🚫	🚫	🚫	🚫
<b>Abrasive</b>								⚙️	⚙️	⚙️
<b>Warps</b>				↓	↓	↓	↓	↓		
<b>Layer adhesion</b>	27 kj/m <sup>2</sup>	86 kj/m <sup>2</sup>	10 kj/m <sup>2</sup>	9 kj/m <sup>2</sup> ↓			4 kj/m <sup>2</sup> ↓	13 kj/m <sup>2</sup>	4 kj/m <sup>2</sup> ↓	5 kj/m <sup>2</sup> ↓
<b>Nozzle / hardened</b>	>=0.4mm	>=0.4mm	>=0.4mm	All	All	>=0.4 ⚙️	>=0.4 ⚙️	>=0.4 ⚙️	>=0.4 ⚙️	>=0.4 ⚙️
<b>Build plate</b>	❄️🔥	🔥	🔥	🔥	🔥	🔥	🔥	🔥	🔥	❄️🔥
<b>Print speed</b>	80mm/s 🚧	200mm/s	250mm/s	300mm/s	300mm/s	100mm/s 🚧	130mm/s	100mm/s 🚧	100mm/s 🚧	100mm/s 🚧
<b>Max Volum flow</b>	3.6mm <sup>3</sup> /s	12mm <sup>3</sup> /s	18mm <sup>3</sup> /s	18mm <sup>3</sup> /s	18mm <sup>3</sup> /s	8mm <sup>3</sup> /s	10.5mm <sup>3</sup> /s	8mm <sup>3</sup> /s	6.5mm <sup>3</sup> /s	8mm <sup>3</sup> /s
<b>Tips</b>	<a href="#">Tips</a>				Resist 🔥	use 0.6mm	use 0.6mm	use 0.6mm	use 0.6mm	use 0.6mm
<b>Annealing</b>	70°C 12h	🚫	70°C 12h	80°C 12h	80°C 12h		80°C 12h	80°C 12h	130°C 12h	80°C 12h